



Product Information

www.miller-stephenson.com

MS-465C / 467C Acrylic Conformal Coating

Description:

A tough, fast drying, abrasion resistant coating providing protection against caustics and corrosives. Methacrylate copolymer resin offers excellent resistance to water, alcohol, dilute acids & alkalis, chemical fumes and corrosive or oxidizing environments. It offers excellent weatherability and superior abrasion resistance. It is solderable for ease of repair.

Allow 48 hours minimum to reach room temperature before using cans stored or received during cold weather.

Application:

Acrylic Conformal Coating is water-white in color and transparency, with high gloss and hardness. It dries in 10 minutes and is fully cured in 24 hours. At a 2 mil. thickness, coverage is approximately 7.6 square feet per 14 oz. aerosol can of MS-465C, and 95 square feet per gallon of MS-467C.

NOTE: DO NOT SHAKE CAN AGGRESSIVELY; INVERT CAN AND PURGE AFTER EVERY USE. Valve and actuator clogging will occur if this is not performed.

Acrylic conformal coating can be removed with MS-114D or MS-115 Conformal Coating Strippers.

Cured Electrical Properties

Dielectric Strength, volts/mil	2000
Dielectric Constant @ 10 ⁵ Hz	3.42
Dissipation Factor @ 10 ⁵ Hz	0.031

Cured Physical Properties

Glass Transition Temperature	168°F/76°C
Tukon Hardness, Knoop No.	13
Acid Number	5
Tensile Strength (23°C/73°F @ 50% RH)	1,600 psi
Elongation at Break (23°C/73°F @ 50 RH)	0.50%
Operating Temperature	23°F/-5°C to 168°F/76°C

VOC Content of MS-465C.....	170 g/l
VOC Content of MS-467C.....	171 g/l

Fluorescent when viewed with ultraviolet light.
Miller-Stephenson offers urethane, acrylic and silicone conformal coatings available in aerosol and bulk liquid.

Safety Data Sheets (SDS) are available upon request.

1437-9M

The recommendation made here with and the information set forth with respect to the performance or use of our products are believed, but not warranted to be accurate. The products discussed are sold without warranty, as to fitness or performance, express or implied and upon condition that purchasers shall make their own test to determine suitability of such products for their particular purposes. Likewise, statements concerning the possible uses of our products are not intended as recommendations to use our products in the infringement of any patent.

For technical information call 800.992.2424 or 203.743.4447
For product sales: CT 800.442.3424, CA 800.771.8161, IL 800.447.4866, Canada 800.307.2199
www.miller-stephenson.com