



Product Information

www.miller-stephenson.com

MS-470C / 472C Urethane Conformal Coating

Description

Urethane Conformal Coating offers superior toughness, abrasion resistance and excellent protection from humidity and organic solvents. Printed circuit boards covered with urethane coating are repairable. Simply heat the coating with a soldering iron to remove the components.

Allow 48 hours minimum to reach room temperature before using cans stored or received during cold weather.

Application

Air dry for 30 minutes. Repeat up to 2-3 coats. The recommended cure schedule is 2 hours at 140°F/ 60°C and a relative humidity of 30% to 50%. If humidity level is less than 30%, place an open container of distilled water in the oven and allow to equilibrate. The alternate cure, at room temperature and a relative humidity of 30% to 50%, will be tack free in one to four hours, semi-hard in one day, and fully cured in seven days.

MS-470C will cover 8.6 square feet @ a 2-mil thickness per 14oz can. MS-472C is available in quarts and gallons for dip, brush, or spray applications and will cover 120 square feet per gallon at a 2-mil thickness.

NOTE: DO NOT SHAKE CAN AGGRESSIVELY; INVERT CAN AND PURGE AFTER EVERY USE. Valve and actuator clogging will occur if this is not performed.

Urethane conformal coating can be removed with MS-114D or MS-115 Conformal Coating Strippers.

Cured Electrical Properties

Dielectric Strength, volts/mil	1200
Dielectric Constant, 10 ⁵ Hz @ 25°C	4.2
Dissipation Factor, 10 ⁵ Hz @ 25°C	0.010
Volume Resistivity (ohm-cm)	2.0 x 10 ¹³

Cured Physical Properties

Operating Temperature: -67°F/-55°C to 230°F/ 110°C

Appearance: No blistering, wrinkling, cracking, or peeling of film, or substrate after thermal shock, or after moisture resistance testing.

Flexibility: No cracking or crazing of film on bending over a 1/8" diameter mandrel.

Fungus Resistance: Non-nutrient per ASTM G21

Fluorescent when viewed with ultraviolet light.

VOC Content of MS-470C.....	882 g/l
VOC Content of MS-472C.....	893 g/l

Fluorescent when viewed with ultraviolet light. Miller-Stephenson offers urethane, acrylic and silicone conformal coatings available in aerosol and bulk liquid.

Safety Data Sheets (SDS) are available upon request.

1520-9M

The recommendation made here with and the information set forth with respect to the performance or use of our products are believed, but not warranted to be accurate. The products discussed are sold without warranty, as to fitness or performance, express or implied and upon condition that purchasers shall make their own test to determine suitability of such products for their particular purposes. Likewise, statements concerning the possible uses of our products are not intended as recommendations to use our products in the infringement of any patent.

For technical information call 800.992.2424 or 203.743.4447
For product sales: CT 800.442.3424, CA 800.771.8161, IL 800.447.4866, Canada 800.307.2199
www.miller-stephenson.com