

# **Product Information**

www.miller-stephenson.com

# ReleaSys<sup>™</sup> 85 Semi-Permanent Mold Release Agent

#### **Description:**

ReleaSys<sup>™</sup> 85 is a highly versatile water-based, semipermanent mold release agent designed to exhibit superior durability, surface adhesion, and minimization of slip-stick. Properly applied, our product develops a long lasting thin-film on the mold surface with minimal mold build-up. The aerosolized formula ensures proper application is achieved without the need for spray equipment. ReleaSys<sup>™</sup> 85 will not interfere with postproduction finishing operation. Benefits of this product include:

- Exceptional release agent durability
- Clean, Non-oily, Non-migrating
- · Ideal for lower complexity molds
- · Improves quality and consistency of molded parts
- Minimizes mold build-up and fouling

#### **Release Agent Applications:**

ReleaSys<sup>™</sup> 85 is formulated to provide unmatched utility in injection and transfer molding with the following materials:

- Plastics
  Elastomers
- Fluoroelastomers EPDM
- Acrylics
- Epoxy

# **Recommended Application Procedure:**

- Clean mold surface thoroughly. Mechanical cleaning such as plastic bead media blasting, followed by chemical cleaning, provides the best surface for application. Removal of all previous mold release agent and contamination is critical.
- Shake can lightly and hold approximately 6-8 inches away from the heated mold surface. Apply a light coat or release agent. NOTE: ReleaSys<sup>™</sup> 85 must be applied to molds at temperatures greater than 212 °F / 100 °C.
- Allow ReleaSys<sup>™</sup> 85 to cure for approximately 3-5 minutes at normal operating temperatures (minimum 132 °C). Multiple light coats can be applied, however this is not normally necessary.

#### **Reapplication:**

When release becomes hesitant, immediately reapply one coat of ReleaSys<sup>™</sup> 85 in the same manner as described previously. Spot touch-ups can also be done on known high wear or geometrically strained areas.

#### **Physical Properties:**

Primary Polymer:.....Thermoset Polysiloxane Appearance:.....White Emulsion Odor:.....None Specific Gravity:.....1.0 g/mL @ 25°C Flash Point.....None

# Storage and Handling:

ReleaSys<sup>™</sup> 85 should be stored in a well ventilated area which is cool and dry. Prior to use, can should be lightly agitated.

ReleaSys<sup>™</sup> 85 should not be used at temperatures above 250 °C or near open flames. Chemical breakdown will occur which will result in the generation of toxic fumes. When spraying, avoid inhalation of mist and exposure to skin. Always wash hands after handling.

#### Shelf-Life

ReleaSys<sup>™</sup> 85 has a shelf-life of 6 months from the date of shipment.

# ReleaSys<sup>™</sup> Product Line:

Miller-Stephenson offers a selection of high performance water-based, semi-permanent release systems to meet your mold process needs. All variants of the ReleaSys<sup>™</sup> Series will deliver higher productivity, lower rejection rates, and higher quality products.

ReleaSys™ Series	Slip	Durability	Releases per Application
85			
88	0000	0000	0000
89			9999
82			9999
			1598-11K

For further technical information call 800.992.2424 or 203.743.4447 For product sales: CT 800.442.3424, CA 800.771.8161, IL 800.447.4866, Canada 800.307.2199 www.miller-stephenson.com Miller-Stephenson logo and ReleaSys™ are trademarks of Miller-Stephenson Chemical Company Inc