

HELOXY™ Epoxy Functional Modifiers



Momentive's epoxy functional product line of HELOXY™ Modifiers offers formulators the ability to choose between monofunctional and polyfunctional glycidyl ethers, and reactive flexibilizers for their formulating needs.

HELOXY Modifiers are epoxy functionalized alcohols, diols, polyols and acids. Momentive offers three classes of HELOXY Modifiers: monofunctional glycidyl ethers, polyfunctional glycidyl ethers and polyfunctional flexibilizers.

The monofunctional HELOXY Modifier products include both aliphatics and aromatics and are primarily utilized as diluents for a variety of epoxy resins.

The polyfunctional HELOXY Modifier products are aliphatics which provide an increase in the chemical resistance and mechanical performance of the system. The cycloaliphatic modifier offers improved UV resistance when compared to an aromatic modifier. The trifunctional modifier increases the crosslink density of a system.

The HELOXY Modifier products that are flexibilizers can improve wetting performance, offer good color properties for outdoor applications, and can increase the impact strength and toughness of a system.

Areas of application for HELOXY Modifiers include formulations for coatings, civil engineering, adhesives, FRP applications, potting and molding.

HELOXY Modifier Advantages

- Improved cured system flexibility
- Increased peel and impact strength
- Increased levels of filler loading
- Improved resin wetting action
- Reduced viscosity and surface tension

At A Glance

HELOXY™ Monofunctional Aliphatic Glycidyl Ethers 4

These low viscosity epoxy functional modifiers made from aliphatic alcohols provide maximum viscosity reduction when blended with liquid epoxy resins. They can enhance the elongation characteristics of an epoxy system.

HELOXY Monofunctional Aromatic Glycidyl Ethers 4

These low viscosity epoxy functional modifiers made from aromatic alcohols provide viscosity reduction when blended with liquid epoxy systems. They can enhance the tensile strength, flexural strength and elongation of an epoxy system without losing chemical resistance qualities.

HELOXY Polyfunctional Glycidyl Ethers 5

These are di- and trifunctional reactive modifiers made from polyols that provide good viscosity reduction yet retain the functionality and crosslink density of an epoxy system. When properly formulated, the Heat Deflection Temperature of a diluted epoxy system can be maintained while also retaining tensile properties and solvent resistance.

HELOXY Polyfunctional Flexibilizers 5

These products are di- and polyfunctional reactive modifiers made from polyols and acids that provide viscosity reduction while imparting flexibility and toughness to an epoxy resin system.

CARDURA™ E10P Glycidyl Ester 5

This product is a glycidyl ester and is a versatile reactive modifier that provides good moisture resistance while lowering viscosity of an epoxy system. It helps to decrease the tendency of the epoxy resin to crystallize.

Chemical Structures 6–7

The Formulator's Choice

Each of these modifiers provides unique benefits for epoxy resin formulators. Specific properties of our epoxy modifiers, as well as the chemical structure and comments about each product's performance, can be found on the technical summary chart. Keep this chart handy for quick reference whenever you require high performance epoxy modifiers. For a detailed review of the performance and handling properties of HELOXY Modifiers, please refer to the "HELOXY Modifier Selection Guide."

For additional information about any or all of these products, visit our website at www.momentive.com/epoxy

Table 1: HELOXY™ Monofunctional Aliphatic Glycidyl Ethers

Product	Chemical Type	Viscosity @ 25°C (cP)	Weight per Epoxide	Color ¹ (max)	Density (lb/gal)	Comments
HELOXY 8	Alkyl C12-C14 Glycidyl Ether	6–9	280–295	< 1	7.5	Excellent dilution efficiency and provides very good elongation characteristics. Very good substrate and filler wetting. Low odor.
HELOXY 61	Butyl Glycidyl Ether	1–2	145–155	< 1	7.7	Modifier with the highest dilution effect, yet minimal loss of physical performance. Allows for increased filler loading and provides good substrate wetting.
HELOXY 116	2-Ethylhexyl Glycidyl Ether	2–4	215–225	< 1	7.6	Excellent dilution efficiency with low volatility. Provides an alternative to BGE.

¹ Gardner Color Scale

Table 2: HELOXY Monofunctional Aromatic Glycidyl Ethers

Product	Chemical Type	Viscosity @ 25°C (cP)	Weight per Epoxide	Color ¹ (max)	Density (lb/gal)	Comments
HELOXY 62	Cresyl Glycidyl Ether	5–10	175–195	< 2	9.0	Efficient diluent with retention of tensile characteristics. High retention of both moisture and chemical resistance. Low volatility.
HELOXY 65	p-tert-Butyl Phenyl Glycidyl Ether	20–30	225–240	< 1	8.5	Moderate dilution efficiency with exceptional moisture and chemical resistance. Good electrical properties with low volatility.

¹ Gardner Color Scale

Table 3: HELOXY™ Polyfunctional Glycidyl Ethers						
Product	Chemical Type	Viscosity @ 25°C (cP)	Weight per Epoxide	Color ¹ (max)	Density (lb/gal)	Comments
HELOXY 48	Trimethylol Propane Triglycidyl Ether	120–180	138–154	< 2	9.6	Trifunctionality increases crosslink density which maintains or increases reactivity. Moderate dilution efficiency. Exceptional retention of HDT and tensile properties as well as chemical resistance.
HELOXY 67	1,4 Butanediol Diglycidyl Ether	10–20	124–137	< 1	9.2	Superior difunctional viscosity reducer with low volatility. Good retention of physical properties and chemical resistance. Useful in water-reducible systems due to observable water solubility.
HELOXY 68	Neopentyl Glycol Diglycidyl Ether	13–25	130–145	< 1	8.9	Good viscosity reduction with minimum loss of properties; difunctional with low volatility. Most widely used viscosity modifier with good chemical resistance. Good wetting and air release properties.
HELOXY 107	Cyclo Hexane Dimethanol Diglycidyl Ether	55–75	155–165	< 2	9.1	Difunctional modifier gives moderate viscosity reduction with minimum loss of properties. Good for chemical resistance as well as applications requiring minimum deformation under load (i.e. superior creep resistance).

¹ Gardner Color Scale

Table 4: HELOXY Flexibilizers						
Product	Chemical Type	Viscosity @ 25°C (cP)	Weight per Epoxide	Color ¹ (max)	Density (lb/gal)	Comments
HELOXY 71	Dimer Acid Diglycidyl Ester	400–900	390–470	< 10	8.2	Improves impact strength and toughness as an epoxy flexibilizer. Provides resistance to thermal shock.
HELOXY 505	Castor Oil Polyglycidyl Ether	250–500	500–650	< 6	8.5	Imparts flexibility, impact and thermal shock resistance. Good low temperature flexibilization performance. Also allows high peel strength for adhesives. Low odor and nonvolatile.

¹ Gardner Color Scale

Table 5: CARDURA™ Glycidyl Ester						
Product	Chemical Type	Viscosity @ 25°C (cP)	Weight per Epoxide	Color ¹ (max)	Density (lb/gal)	Comments
CARDURA E10P	Neodecanoic Acid Glycidyl Ester	5–10	235–244	≤ 35	8.0	Good dilution efficiency and excellent water resistance characteristics. Helps to decrease the tendency of the epoxy resin to crystallize. Low volatility.

¹ Platinum-Cobalt Color Scale

Table 6: HELOXY™ Monofunctional Aliphatic Glycidyl Ethers		
Product	Chemical Type	Structure
HELOXY Modifier 8	Alkyl C12-C14 Glycidyl Ether	$R-O-CH_2-\overset{\text{O}}{\text{C}}-CH_2$ $R=C_{12}-C_{14}$
HELOXY Modifier 61	Butyl Glycidyl Ether	$CH_3-(CH_2)_2-CH_2-O-CH_2-\overset{\text{O}}{\text{C}}-CH_2$
HELOXY Modifier 116	2-Ethylhexyl Glycidyl Ether	$CH_3-(CH_2)_3-\overset{\text{CH}_3-\text{CH}_2}{\text{CH}}-CH_2-O-CH_2-\overset{\text{O}}{\text{C}}-CH_2$

Table 7: HELOXY Monofunctional Aromatic Glycidyl Ethers		
Product	Chemical Type	Structure
HELOXY Modifier 62	Cresyl Glycidyl Ether	$\text{C}_6\text{H}_4(\text{CH}_3)-O-CH_2-\overset{\text{O}}{\text{C}}-CH_2$
HELOXY Modifier 65	p-tert-Butylphenyl Glycidyl Ether	$(\text{CH}_3)_3\text{C}-\text{C}_6\text{H}_4-O-CH_2-\overset{\text{O}}{\text{C}}-CH_2$

Table 8: HELOXY Polyfunctional Glycidyl Ethers		
Product	Chemical Type	Structure
HELOXY Modifier 48	Trimethylol Propane Triglycidyl Ether	$CH_3-CH_2-C(CH_2-O-CH_2-\overset{\text{O}}{\text{C}}-CH_2)_3$
HELOXY Modifier 67	1,4 Butanediol Diglycidyl Ether	$\overset{\text{O}}{\text{C}}-CH_2-CH_2-O-CH_2-(CH_2)_2-CH_2-O-CH_2-\overset{\text{O}}{\text{C}}-CH_2$
HELOXY Modifier 68	Neopentyl Glycol Diglycidyl Ether	$\overset{\text{O}}{\text{C}}-CH_2-CH_2-O-CH_2-C(\text{CH}_3)_2-CH_2-O-CH_2-\overset{\text{O}}{\text{C}}-CH_2$
HELOXY Modifier 107	Cyclohexane Dimethanol Diglycidyl Ether	$\overset{\text{O}}{\text{C}}-CH_2-CH_2-O-CH_2-\text{C}_6\text{H}_{10}-CH_2-O-CH_2-\overset{\text{O}}{\text{C}}-CH_2$

Table 9: HELOXY™ Flexibilizers		
Product	Chemical Type	Structure
HELOXY Modifier 71	Dimer Acid Diglycidyl Ester	$\text{CH}_2\text{-CH}(\text{O})\text{-CH}_2\text{-O-C(=O)-C}_{34}\text{-C(=O)-O-CH}_2\text{-CH}(\text{O})\text{-CH}_2$
HELOXY Modifier 505	Castor Oil Polyglycidyl Ether	$\begin{array}{c} \text{CH}_2\text{-O-C(=O)-(CH}_2\text{)}_7\text{-CH=CH-CH}_2\text{-CH}(\text{O-CH}_2\text{-CH(O)-CH}_2\text{)}\text{-(CH}_2\text{)}_5\text{-CH}_3 \\ \\ \text{CH-O-C(=O)-(CH}_2\text{)}_7\text{-CH=CH-CH}_2\text{-CH}(\text{O-CH}_2\text{-CH(O)-CH}_2\text{)}\text{-(CH}_2\text{)}_5\text{-CH}_3 \\ \\ \text{CH}_2\text{-O-C(=O)-(CH}_2\text{)}_7\text{-CH=CH-CH}_2\text{-CH}(\text{O-CH}_2\text{-CH(O)-CH}_2\text{)}\text{-(CH}_2\text{)}_5\text{-CH}_3 \end{array}$

Table 10: CARDURA™ Glycidyl Ester		
Product	Chemical Type	Structure
CARDURA E10P	Neodecanoic Acid Glycidyl Ester	$\begin{array}{c} \text{R}^1 \text{ O} \\ \quad \\ \text{R}^2\text{-C-C-O-CH}_2\text{-CH}(\text{O})\text{-CH}_2 \\ \\ \text{R}^3 \end{array} \quad \text{R}^1=1, \text{R}^2+\text{R}^3=7$

Safety, Storage and Handling

Please refer to the Material Safety Data Sheet (MSDS) for the most current Safety and Handling information. Please refer to the Momentive website for shelf life and recommended storage information.

Exposure to these materials should be minimized and avoided, if feasible, through the observance of proper precautions, use of appropriate engineering controls and proper personal protective clothing and equipment, and adherence to proper handling procedures. **None of these materials should be used, stored or transported until the handling precautions and recommendations as stated in the MSDS for these and all other products being used are understood by all persons who will work with them.** Questions and requests for information on Momentive Specialty Chemicals Inc. ("Momentive") products should be directed to your Momentive sales representative, or the nearest Momentive sales office. Information and MSDSs about non-Momentive products should be obtained from the respective manufacturer.

Packaging

Available in bulk and drum quantities.

Contact Information

For product prices, availability or order placement, call our toll-free customer service number at +1 866 443 9466.

For literature and technical assistance, visit our website at www.momentive.com/epoxy

Momentive: The Science Behind What Lies Ahead

At Momentive, our global team is focused on delivering value by helping our customers make their products and processes better. We do this by bringing our deep technical expertise, market experience and technology portfolio to bear on their specific challenges. We are the science behind thousands of innovations that enhance both our customers' business results...and everyday life.

Reach our Global Customer Service network at:

U.S. and Canada **+1 888 443 9466**
E-mail: 4information@momentive.com

Europe **+800 836 43581**
E-mail: 4information.eu@momentive.com

All Others **+86 21 3860 4638**

Please refer to the literature code MSC-154 when contacting us.



Momentive Specialty Chemicals Inc.

World Headquarters

180 East Broad Street
Columbus, OH 43215-3799

© 2012 Momentive Specialty Chemicals Inc. All rights reserved.
© and ™ denote trademarks owned by or licensed to Momentive Specialty Chemicals Inc.

MSC-154 4/12 Printed in U.S.A.

The information provided herein was believed by Momentive Specialty Chemicals ("Momentive") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Momentive are subject to Momentive's terms and conditions of sale. MOMENTIVE MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY MOMENTIVE, except that the product shall conform to Momentive's specifications. Nothing contained herein constitutes an offer for the sale of any product.