



# Product Information

[www.miller-stephenson.com](http://www.miller-stephenson.com)

## MS-487G RFI Nickel Conductive Coating

### Description

An excellent way to limit EMI/RFI emissions is with a Milshield Conductive Coating. MS-487G is a black coating, which may be applied in a 2 mil layer to absorb EMI/RFI over a broad frequency range. This coating can be used effectively with Acrylic, Polycarbonate, ABS, Polystyrene, PVC and other plastics.

Agitate material before and during use to prevent settling of the active ingredients. Apply to a clean, dry surface in a well-ventilated area at temperatures between 70-85°F.

### APPLICATIONS:

MS-487G can be applied by dipping or brushing. Do not spray. 1-2 coats will provide approximately 1.5-2.0 mil coating. Allow each coating to dry for 30 minutes before applying another coat. Do not dilute or contaminate with water.

### PHYSICAL PROPERTIES:

**Surface Resistivity** (ASTM D-257): 0.7 ohm/sq.

**Adhesion on polycarbonate** (ASTM D-3359): 3

**Static Decay** (5000 volts to zero): Instantaneous

### Attenuation

(IEEE 299-2006 modified using a Duel TEM Cell)

- 1 mHz: 51.0 dB
- 10 mHz: 58.8 dB
- 100 mHz: 38.9 dB
- 1000 mHz: 57.3 dB

### ELASTOMER COMPATIBILITY:

(Immersion: 15 mins at Room Temperature)

• Butyl Rubber	• Natural Rubber
• Polysulfide	• EPDM
• Buna S	• Buna N
• Neoprene	• Urethane
• Chlorosulfonated PE	• Silicone
• Viton™	

**NOTE:** Elastomer swelling and shrinking will, in most cases, revert to within a few percent of original size after air drying. Swell, shrinkage, and extractables are strongly affected by the compounding agents, plasticizers, and curing used in the manufacture of the elastomers. Test for compatibility before use.

### METAL COMPATIBILITY:

(Immersion: 2 weeks at 99°F/37°C)

- Aluminum
- Copper
- Iron
- Steel

**Note:** Test for compatibility before use.

**Safety Data Sheet (SDS) is available upon request.**

Viton™ is a trademark of The Chemours Company FC, LLC

**LIMITATION OF LIABILITY AND REMEDIES:** Manufacturer warrants that, at the time of shipment by the Manufacturer, this product is free from defect in material and manufacture. If the product is proved to be defective, the exclusive remedy, at Manufacturer's option, shall be refund of the purchase price or replacement of the defective product, provided written notice of the defect is given no later than one year after the date of shipment by the Manufacturer. Manufacturer shall not otherwise be liable for loss or damages whether direct, indirect, incidental or consequential, regardless of the legal theory asserted, including negligence and strict liability. **Manufacturer expressly disclaims all implied warranties, including the implied warranty of merchantability and the implied warranty of fitness for a particular purpose. There are no warranties which extend beyond the description on the face hereof.**

1452-12N

For technical information call 800.992.2424 or 203.743.4447

For product sales: CT 800.442.3424, CA 800.771.8161

[www.miller-stephenson.com](http://www.miller-stephenson.com)

miller-stephenson logo is a trademark of miller-stephenson chemical company inc