



# Product Information

[www.miller-stephenson.com](http://www.miller-stephenson.com)

## MS-530N/532N Contact Re-Nu®

### Description:

A cleaning agent that restores electrical or mechanical continuity on all types of contacts. Excellent for cleaning oxides, oil, grease and dust from contacts, switches, relays, tuners, encoders, slide wires, rheostats, distribution panels and servomechanisms. Evaporates quickly and leaves no residue.

### Advantages:

- High effective cleaning agent
- Evaporates quickly
- Nonflammable
- Leaves no residue
- RoHS compliant

### Typical Properties:

Boiling Point..... 98°F /37°C  
Liquid Density.....1.26 g/ml @ 77°F/25°C  
Ozone Depletion.....0.00  
VOC Content of MS-530N.....420g/l  
VOC Content of MS-532N.....372g/l

### Plastic Compatibility:

(Immersion: 15 minutes at Room Temperature)

- Acetal
- Polypropylene
- PEK, PEEK
- Polyimides
- PTFE
- Polyethylene
- Polyester, PBT, PET
- Epoxy-Phenolcs
- Polyvinylchloride
- Liq. Crystal Polymer

**NOTE:** Acrylics, ABS, and polycarbonate, if under stress, may show slight cracking or crazing damage. Test for compatibility before use.

### Elastomer Capability:

(Immersion: 15 mins at Room Temperature)

- Butyl Rubber
- Polysulfide
- Buna S
- Neoprene
- Chlorosulfonated PE
- Viton™
- Natural Rubber
- EPDM
- Buna N
- Urethane
- Silicone

**NOTE:** Elastomer swelling and shrinking will, in most cases, revert to within a few percent of original size after air drying. Swell, shrinkage, and extractables are strongly affected by the compounding agents, plasticizers, and curing used in the manufacture of the elastomers. Test for compatibility before use.

### Metal Compatibility:

(Immersion: 2 weeks at 99°F/37°C)

- Aluminum
- Copper
- Iron

**Note:** Test for compatibility before use.

### Safety Data Sheets (SDS) are available upon request

Viton™ is a trademark of The Chemours Company FC, LLC  
Contact Re-Nu® is a registered trademark of miller-stephenson chemical co inc  
miller-stephenson logo is a trademark of miller-stephenson chemical co inc

1603-9M

The recommendation made here with and the information set forth with respect to the performance or use of our products are believed, but not warranted to be accurate. The products discussed are sold without warranty, as to fitness or performance, express or implied and upon condition that purchasers shall make their own test to determine suitability of such products for their particular purposes. Likewise, statements concerning the possible uses of our products are not intended as recommendations to use our products in the infringement of any patent.

For technical information call 800.992.2424 or 203.743.4447  
For product sales: CT 800.442.3424, CA 800.771.8161, IL 800.447.4866, Canada 800.307.2199  
[www.miller-stephenson.com](http://www.miller-stephenson.com)