



# Product Information

www.miller-stephenson.com

## MS-122SEL High Performance Mold Release Agent

### Description:

MS-122SEL is a Low Global Warming (LGW) formulation that has high performance, high solvency mold release agent utilizing PTFE fluoropolymers (polytetrafluoroethylene) specifically designed for unsurpassed adhesion to mold surfaces and extended durability. The proprietary solvent blend ensures that proper wetting, leveling, and surface preparation occurs when applied yielding a durable, uniform thin-film. MS-122SEL offers the following benefits:

- Superior adhesion to mold surfaces
- High Solvency/Rapid Evaporating Carrier Fluid
- Ideal for compression/injection molding
- Nonflammable; Non-ozone depleting formulation
- Non-migrating; Non-staining

### Release Agent Applications:

MS-122SEL can be used to release the following materials:

- Plastics
- Resins
- Acrylics
- Urethanes
- Nylons
- Rubbers
- Phenolics
- Polycarbonates
- Polystyrene
- Elastomers

### Recommended Application Procedure:

1. Clean mold surface thoroughly. Mechanical cleaning such as, bead media blasting or steel wool, followed by chemical cleaning, provides the best surface for application of 122SEL. Removal of all previous mold release agent is critical.
2. Shake can vigorously for one minute. Hold can approximately 6-8 inches away from a non-heated mold surface, and apply a light coat of release agent. NOTE: Material will apply wet and transparent, but will dry to a fine-white coat.
3. Allow solvent to dry completely before molding any parts. This will ensure the most effective coating for durability and cycle life.

### Reapplication:

1. When release becomes hesitant, reapply one coat of MS-122SEL in the same manner as described above.

### Fused Coatings Procedure (Optional)

1. After applying the release agent, heat the surface to 581°F - 600°F.
2. Coating transition from a white to translucent will occur. Maintain the temperature of the coated surface for 5 to 10 minutes.
3. If a white residue is left on the metal surface, buff with a soft cloth. When the coating is properly fused, it is extremely durable.

### Physical Properties:

Primary Polymer:.....Fluoropolymer  
 Appearance:.....White Particle suspension  
 Odor:.....Slight  
 Specific Gravity:.....1.41 g/mL @ 25°C  
 VOC Content.....550 g/l

### MS-122 Product Line:

Miller-Stephenson offers a selection of specialized formulations which provide high performance solutions for your molding process. All variants of the MS-122 Series will deliver higher productivity, lower rejection rates, and higher quality products. Please use the product selection guide below to help direct you to the appropriate product.

MS-122 Series	Dry Time	Durability	Releases per Application
AD	●●	●	●
XD	●●●●	●●	●●
AV	●	●●●●	●●●●
SE	●●●●	●●●●	●●●●

Safety data sheet (SDS) available upon request.

1607-10M

The recommendation made here with and the information set forth with respect to the performance or use of our products are believed, but not warranted to be accurate. The products discussed are sold without warranty, as to fitness or performance, express or implied and upon condition that purchasers shall make their own test to determine suitability of such products for their particular purposes. Likewise, statements concerning the possible uses of our products are not intended as recommendations to use our products in the infringement of any patent.

For technical information call 800.992.2424 or 203.743.4447

For product sales: CT 800.442.3424, CA 800.771.8161, IL 800.447.4866, Canada 800.307.2199

www.miller-stephenson.com