


Product Information

Krytox™ oils and greases are based on perfluoropolyether (PFPE) oils. Chemically inert and safe for use around most chemicals and reactive gases, these lubricants are nonflammable and are also safe for use in oxygen service. Krytox™ oils and greases are compatible with commonly used materials and do not damage plastics or elastomers, nor cause corrosion to metals.

Krytox™ oils and greases are commonly used as lubricants in aerospace, automotive, industrial, and semiconductor applications, as well as in solving many other routine lubrication problems. In addition, they provide exceptionally long lifetimes in sealed-for-life bearings and can extend re-lubrication intervals in bearings that require re-lubrication.

Krytox™ base oil is a clear, colorless, fluorinated synthetic oil; it is a PFPE, but is also called perfluoroalkylether (PFAE) or perfluoropolyalkylether (PFPAE) with the following chemical structure:



The polymer chain is completely saturated and contains only carbon, oxygen, and fluorine. On a weight basis, a typical Krytox™ oil contains 21.6% carbon, 9.4% oxygen, and 69.0% fluorine.

Krytox™ GPL 203 Lubricant

Krytox™ GPL 203 grease is polytetrafluoroethylene (PTFE)-thickened, contains no additives, and can be used on components that come in contact with chemicals. Typical applications include valves, instruments, or bearings that come into contact with chemicals, such as alcohols, ammonia, solvents, steam, acids and bases, and oxygen systems, e.g., LOX¹ and GOX². Krytox™ GPL 203 grease is commonly used as a lubricant for seals and O-rings, and is compatible with most types of seals.

Krytox™ oils and greases are silicone-free. They do not contain any VOC³ materials or chlorine and are not hazardous to the atmosphere or ozone layer. They are biologically and environmentally inert.

¹LOX = Liquid oxygen
²GOX = Gaseous oxygen
³VOC = Volatile organic compounds

Typical Properties of Krytox™ GPL 203

Anti-Corrosion Additive	No
Appearance	White, creamy consistency
Estimated Useful Temperature Range, °C (°F)	-60-154 (-76-310)
Base Oil Viscosity, cSt, 20 °C (68 °F)	82
40 °C (104 °F)	30
100 °C (212 °F)	5
Oil Separation, % in weight after 30 hr, 99 °C (210 °F)	6
Maximum Oil Volatility, % in 22 hr, 66 °C (150 °F)	1
D2595, 121 °C (250 °F)	7
Dropping Point	NA
Standard NLGI Grade	2
Specific Gravity, g/cm ³	1.97
Food Contact Approval	Yes, NSF H-1

These values are typical properties and not specifications.

The high-temperature stability of fully fluorinated Krytox™ lubricants improves bottom-line savings from improved reliability as well as reduced grease usage and manpower through extended re-lubrication intervals. Excellent film strength reduces wear to reduce maintenance costs. Under high loads, the viscosity increases to provide support and absorb pressure.

Typical Applications

Applications for these lubricants are generally of a critical nature. Temperatures in all industries are reaching extremes for conventional lubricants; lubricants are expected to be durable in the most aggressive environments and are now often considered an integral part of the design. Where extreme conditions and extreme performance demands prevail, whether because of durability, warranty, safety, loss of productivity, or downtime, Krytox™ lubricants are the ideal choice in a wide range of industries and applications.

Preparing the Bearings

New, unlubricated bearings often have rust-preventive oils in them to prevent damage while they are in storage prior to use. Before using new bearings, they should be inspected for damage and cleanliness*. When preparing to use Krytox™ lubricant, greases or preservative oils need to be removed.

*For guidelines on bearing preparation, ask for literature item no. K-22116-1, "New Bearing Preparation."

Failure to do so could result in reduced bearing life. Bearing life tests on uncleaned bearings have shown reduced life in high temperature, high-speed tests where the bearing was filled with a minimum amount of grease. The preservatives coat the metal surface to prevent rusting; therefore, they can also prevent the grease from adhering, causing them to be thrown off by the action of the bearing. The preservatives could also oxidize and harden, and create debris that will contaminate the new grease.

Storage and Shelf Life

Because of the inert, non-oxidizing nature of the ingredients, Krytox™ lubricants have an indefinite shelf life if unopened and stored in a clean dry location. Greases might show oil separation after extended storage, but mixing the free oil back into the grease will return the grease to its normal usable condition.

The information set forth herein is furnished free of charge and based on technical data that Chemours believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, Chemours makes no warranties, express or implied, and assumes no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF CHEMOURS.

For product information, industry applications, technical assistance, or global distributor contacts, visit krytox.com or within the U.S. and Canada, call 1-844-773-CHEM/2436 or outside of the U.S., call 1-302-773-1000.

© 2015 The Chemours Company FC, LLC. Krytox™ and any associated logos are trademarks or copyrights of The Chemours Company FC, LLC. Chemours™ and the Chemours Logo are trademarks of The Chemours Company.

Replaces: K-23315-2
C-10350 (10/15)