

## MS-111 Epoxy Stripping Agent

### Description:

MS-111 will readily soften and strip most organic systems, such as epoxies and polyurethanes. It will not attack any metal surfaces or valuable parts during the time necessary to remove polymers. Caution: It may darken stainless steel and aluminum.

This product has not been tested on specific epoxy and polyurethane systems.

### Advantages:

- Nonflammable
- Low in viscosity
- Free rinsing in alcohol
- Available in quart and gallon container(s)

### Physical Properties:

|                |                      |
|----------------|----------------------|
| Color          | Light to dark amber  |
| Boiling point  | 104°F/40°C           |
| Vapor pressure | 340 mmHg @ 68°F/20°C |
| Form           | Liquid               |
| VOC Content    | 275 g/l              |

### Directions for use:

Vent containers carefully to equalize pressure and pour material carefully at room temperature to avoid splashing and boiling. MS-111 is to be used at room temperature.

**Coatings:** MS-111 may be applied with a brush containing only non-plastic bristles and handle. When film has lifted, either scrape or rinse with alcohol. A second application will occasionally prove necessary.

**Castings:** Place object to be stripped in tank, cover with liquid, and allow to stand until plastic has disintegrated or loosened. This will vary from minutes to days depending on casting thickness. Remove with a hook or basket. Flush with clean alcohol.

It is recommended to test for compatibility for surfaces that are not to be stripped.

### Storage:

MS-111 should be stored at/or below room temperature in a glass or polyethylene container, which should be tightly closed to retard evaporation. MS-111 should be used as soon as practicable and not stored for prolonged periods in other than original container or glass. Keep tightly sealed.

**Safety Data Sheet (SDS) is available upon request.**

**LIMITATION OF LIABILITY AND REMEDIES:** Manufacturer warrants that, at the time of shipment by the Manufacturer, this product is free from defect in material and manufacture. If the product is proved to be defective, the exclusive remedy, at Manufacturer's option, shall be refund of the purchase price or replacement of the defective product, provided written notice of the defect is given no later than one year after the date of shipment by the Manufacturer. Manufacturer shall not otherwise be liable for loss or damages whether direct, indirect, incidental or consequential, regardless of the legal theory asserted, including negligence and strict liability. **Manufacturer expressly disclaims all implied warranties, including the implied warranty of merchantability and the implied warranty of fitness for a particular purpose.** There are no warranties which extend beyond the description on the face hereof.

1454-11R